

भारत का राजपत्र The Gazette of India

प्रसाधारण

EXTRAORDINARY

भाग II—खण्ड 3—उप-खण्ड (ii)

PART II—Section 3—Sub-section (ii)

प्राधिकार से प्रकाशित

PUBLISHED BY AUTHORITY

सं० 359] नई दिल्ली, बुधवार, अक्टूबर 3, 1968/आश्विन 11, 1890
No. 359] NEW DELHI, THURSDAY, OCTOBER 3, 1968/ASVINA 11, 1890

इस भाग में भिन्न पृष्ठ संख्या दी जाती है जिससे कि यह अलग संकलन के रूप में रखा जा सके।

Separate paging is given to this Part in order that it may be filed as a separate compilation.

MINISTRY OF COMMERCE

NOTIFICATION

New Delhi, the 3rd October 1968

S.O. 3501.—Whereas the Central Government is of opinion that in exercise of the powers conferred by section 6 of the Export (Quality Control and Inspection) Act, 1963 (22 of 1963), it is necessary or expedient to amend the notification of the Government of India in the Ministry of Commerce No. S.O. 1616, dated the 7th May, 1968, in the manner specified below for the development of the Export trade of India and has forwarded the proposal in that behalf to the Export Inspection Council, as required by sub-rule (2) of rule 11 of the Export (Quality Control and Inspection) Rules, 1964:

Now, therefore, in pursuance of the said sub-rule the Central Government hereby publishes the said proposal for the information of the public likely to be affected thereby.

2. Notice is hereby given that any person desiring to forward any objections or suggestions with respect to the said proposal may forward the same within thirty days of the date of publication in the Gazette of India of this notification to the Export Inspection Council, World Trade Centre, 14/1-B, Ezra Street (7th floor), Calcutta-1.

Proposals

The notification of the Government of India in the Ministry of Commerce No. S.O. 1616, dated the 7th May, 1968, shall be amended as follows, namely:—

In the Annexure to the said notification under the heading "A. Specification for refills" for clause 5, the following clause shall be substituted, namely:—

"5. The thermal shock resistance of the refill shall be considered adequate if the refill suffers no damage when subject to the following test:

Pour water at $27^{\circ} \pm 2^{\circ}\text{C}$ upto the neck of the refill and allow to stand for 3 minutes. Empty the refill and immediately pour boiling water

(100°C) and allow to stand for 3 minutes. Empty the refill and pour water at $27^{\circ} \pm 2^{\circ}\text{C}$ immediately and allow to stand for 3 minutes. The time for pouring water in and out shall not exceed 15 seconds in each case."

[No. 60(40)Exp.Insp/67.]

A. C. BANERJEE, Jt. Secy.